

测试报告

Test report



Verify Report

24G-000748(A3)

结论

Overall result

所有检测项目符合标准要求

PASS

备注：本检测结论是对所有检测项目是否符合标准要求进行的判定，检测结果详见后页。

The overall result is given based on all the tests conducted in this report. Please refer to the following pages for test result summary and notes.

客户信息

Client information

客户名称：Karl Josef Schmied Lederwarencreation
Client: Gmbh
地址：Marienstraße 11A, Dieburg, Germany
Address: 64807



样品信息

Sample information

样品描述：Audi Ladies collection

Description:

SKU 号/款号：Item 315 240 0200 wallet with wrist strap

SKU/style #: Item 315 240 0300 phone pouch

Item 315 240 0400 small wallet

Item 318 240 0100 lanyard

Item 318 240 0200 key ring

原产地：-

Country of origin:

发行/销售地区：China

Country of distribution:

收样数量：6 sets + 1 lot parts

Quantity submitted:

订单编号：-

Purchase order #:

产品标识年龄：-

Labeled age grade:

实际测试年龄：-

Tested age grade:

基本信息

General information

样品接收日期：2024 年 2 月 4 日

Sample receipt date: 04-Feb-2024

测试周期：2024 年 2 月 4 日 至

Testing period: 2024 年 2 月 21 日

04-Feb-2024 to 21-Feb-2024

报告发布日期：2024 年 2 月 21 日

Report date: 21-Feb-2024



Verify Report

启迈瀚莎检测服务（东莞）有限公司
广东省东莞市寮步镇长坑长圣路 6 号 1 栋
101 室

QIMA Hansecontrol Testing Service (Dongguan) Co. Ltd.
Room 101, Building 1, No. 6, Changsheng Road, Changkeng,
Liaobu Town, Dongguan City, 523400 Guangdong, P.R.China

support@qima.com • ©QIMA Limited
DGN-TS-RE-042 ver. 1.2
Page 1 of 20



报告编号
Test report #
24G-000748(A3)

报告发布日期
Report date
2024 年 2 月 21 日
21-Feb-2024

基本信息

General information

启迈瀚莎检测服务（东莞）有限公司
QIMA Hansecontrol Testing Service (Dongguan) Co. Ltd.

王锡健
化学实验室有机&无机组长

启迈瀚莎检测服务（东莞）有限公司
QIMA Hansecontrol Testing Service (Dongguan) Co. Ltd.

叶俊炯
纺织实验室主管

启迈瀚莎检测服务（东莞）有限公司
QIMA Hansecontrol Testing Service (Dongguan) Co. Ltd.

报告签署人姓名
物理实验室经理



Verify Report

启迈瀚莎检测服务（东莞）有限公司
广东省东莞市寮步镇长坑长圣路 6 号 1 栋
101 室

QIMA Hansecontrol Testing Service (Dongguan) Co. Ltd.
Room 101, Building 1, No. 6, Changsheng Road, Changkeng,
Liaobu Town, Dongguan City, 523400 Guangdong, P.R.China

support@qima.com • ©QIMA Limited
DGN-TS-RE-042 ver. 1.2
Page 2 of 20



测试结果汇总 Result summary

根据客户的要求，详细的测试项目如下：
At the request of the client, the following test were conducted:

测试项目 Test(s) conducted	结论 Conclusion
QB/T 1619-2018-票夹 - 甲醛含量的测定	合格
QB/T 1619-2018-Wallet, Formaldehyde	PASS
QB/T 1619-2018-票夹 - 禁用偶氮染料的测定	合格
QB/T 1619-2018-Wallet, Azocolorants	PASS
QB/T 1619-2018-票夹-配件质量 ^Φ	合格
QB/T 1619-2018-Wallet-Accessories Quality ^Φ	PASS
QB/T 1619-2018 票夹-条款 5.1.5 五金配件 ^Φ	合格
QB/T 1619-2018 -Wallet -Clause 5.1.5 Hardware Fitting Properties ^Φ	PASS
QB/T 1619-票夹-外观质量和缝制要求	合格
QB/T 1619-Wallet-Appearance Quality	PASS
QB/T 1619-票夹-拉链耐用度	合格
QB/T 1619-Wallet-Zipper Durability (200 cycles)	PASS
QB/T 1619-票夹-皮革摩擦色牢度	合格
QB/T 1619-Wallet-Colorfastness to Rotary Rubbing in Leather	PASS
QB/T 1619-票夹-纺织材料摩擦色牢度	合格
QB/T 1619-Wallet-Colorfastness to Rubbing in Textiles	PASS

注释：
Note:
测试项目标记 ‘^Φ’ 表示此项目由外部实验室完成。
Test(s) marked with ‘^Φ’ indicate tests performed in external laboratories.

根据客户的要求，对选定的组件进行了测试
By client's request, selected components were tested.

本检测报告仅用于客户科研、教学、内部质量控制、产品研发等目的，仅供内部参考。
This report is for client internal use only such internal scientific research, education, quality control, product R&D.





详细结果
Detailed results

QB/T 1619-2018-票夹 - 甲醛含量的测定
QB/T 1619-2018-Wallet, Formaldehyde

测试方法: GB/T 2912.1-2009
Test Method:
测试仪器: 紫外分光光度计
Analytical Method: Ultraviolet-Visible Spectrophotometry

样品编号 Specimen No.	3+4+5	6	8	---	限值 Limit (mg/kg)
测试项目 Test Item CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
甲醛 Formaldehyde 50-00-0	未检出 ND	18	未检出 ND	---	75
结论 Conclusion	PASS 合格	PASS 合格	PASS 合格	---	

备注:
Note:
mg/kg =毫克每千克
mg/kg = Milligrams per kilogram
LT =少于
LT = Less than
ND =未检出 (报告检出限= 16 mg/kg)
ND = Not detected (Reporting Limit = 16 mg/kg)





详细结果
Detailed results

QB/T 1619-2018-票夹 - 甲醛含量的测定
QB/T 1619-2018-Wallet, Formaldehyde

测试方法: GB/T 19941.1-2019
Test Method:
测试仪器: 高效液相色谱仪
Analytical Method: High Performance Liquid Chromatography

样品编号 Specimen No.	1+2	---	---	---	限值 Limit (mg/kg)
测试项目 Test Item CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
甲醛 Formaldehyde 50-00-0	未检出 ND	---	---	---	75
结论 Conclusion	PASS 合格	---	---	---	

备注:
Note:
mg/kg =毫克每千克
mg/kg = Milligrams per kilogram
LT =少于
LT = Less than
ND =未检出 (报告检出限= 16 mg/kg)
ND = Not detected (Reporting Limit = 16 mg/kg)



详细结果

Detailed results

QB/T 1619-2018–票夹– 禁用偶氮染料的测定

QB/T 1619-2018-Wallet, Azocolorants

测试方法:

Test Method:

测试仪器:

Analytical Method:

GB/T 17592-2011, GB/T 23344-2009

气相色谱-质谱联用仪/液相色谱-质谱联用仪

Gas Chromatography with Mass Spectrometry/ Liquid Chromatography with Mass Spectrometry

样品编号 Specimen No.		3+4+5	8	---	---	限值 Limit (mg/kg)
测试项目 Test Item	CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
4-氨基联苯 4-aminobiphenyl	92-67-1	未检出 ND	未检出 ND	---	---	30
联苯胺 Benzidine	92-87-5	未检出 ND	未检出 ND	---	---	30
4-邻氯甲苯胺 4-chloro-o-toluidine	95-69-2	未检出 ND	未检出 ND	---	---	30
2-萘胺 2-naphtylamine	91-59-8	未检出 ND	未检出 ND	---	---	30
邻氨基偶氮甲苯 o-aminoazotoluene	97-56-3	未检出 ND	未检出 ND	---	---	30
5-硝基-邻甲苯胺 5-nitro-o-toluidine	99-55-8	未检出 ND	未检出 ND	---	---	30
对氯苯胺 p-chloroaniline	106-47-8	未检出 ND	未检出 ND	---	---	30
二氨基苯甲醚 2,4-diaminoanisole	615-05-4	未检出 ND	未检出 ND	---	---	30
4, 4-二氨基二苯甲烷 4,4'-diaminodiphenyl methane	101-77-9	未检出 ND	未检出 ND	---	---	30
3, 3-二氯联苯胺 3,3'-dichlorobenzidine	91-94-1	未检出 ND	未检出 ND	---	---	30
3, 3-二甲氧基联苯胺 3,3'-dimethoxybenzidine	119-90-4	未检出 ND	未检出 ND	---	---	30
3, 3-二甲基联苯胺 3,3'- dimethylbenzidine	119-93-7	未检出 ND	未检出 ND	---	---	30
3, 3-二甲基-4, 4-二氨 基二苯甲烷 3,3'-dimethyl-4,4'- diaminodiphenyl methane	838-88-0	未检出 ND	未检出 ND	---	---	30
2-甲氧基-5-甲基苯胺 p- cresidine	120-71-8	未检出 ND	未检出 ND	---	---	30

样品编号 Specimen No.		3+4+5	8	---	---	限值 Limit (mg/kg)
测试项目 Test Item	CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
4, 4-次甲基双（2-氯苯胺） 4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	未检出 ND	未检出 ND	---	---	30
4, 4-二氨基二苯醚 4,4'-oxydianiline	101-80-4	未检出 ND	未检出 ND	---	---	30
4, 4-二氨基二苯硫醚 4,4'-thiodianiline	139-65-1	未检出 ND	未检出 ND	---	---	30
邻甲苯胺 o-toluidine	95-53-4	未检出 ND	未检出 ND	---	---	30
2, 4-二氨基甲苯 2,4-toluylenediamine	95-80-7	未检出 ND	未检出 ND	---	---	30
2, 4, 5-三甲基苯胺 2,4,5-trimethylaniline	137-17-7	未检出 ND	未检出 ND	---	---	30
邻茴香胺 o-anisidine	90-04-0	未检出 ND	未检出 ND	---	---	30
2,4-二甲基苯胺 2,4 - xyldine	95-68-1	未检出 ND	未检出 ND	---	---	30
2,6-二甲基苯胺 2,6 - xyldine	87-62-7	未检出 ND	未检出 ND	---	---	30
结论 Conclusion		PASS 合格	PASS 合格	---	---	

备注：
Note:
mg/kg =毫克每千克
mg/kg = milligrams per kilogram
LT =少于
LT = Less than; MT = More than
ND = 未检出 (报告检出限 = 5 mg/kg)
ND = Not detected (Reporting limit = 5 mg/kg)
混测结果基于样品的总质量来进行计算。
Composite results are based on total mass of the composite test portion.

详细结果

Detailed results

QB/T 1619-2018–票夹– 禁用偶氮染料的测定

QB/T 1619-2018-Wallet, Azocolorants

测试方法:

Test Method:

GB/T 19942-2019

测试仪器:

Analytical Method:

气相色谱-质谱联用仪/液相色谱-质谱联用仪

Gas Chromatography with Mass Spectrometry/ Liquid Chromatography with Mass Spectrometry

样品编号 Specimen No.		1+2	---	---	---	限值 Limit (mg/kg)
测试项目 Test Item	CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
4-氨基联苯 4-aminobiphenyl	92-67-1	未检出 ND	---	---	---	30
联苯胺 Benzidine	92-87-5	未检出 ND	---	---	---	30
4-邻氯甲苯胺 4-chloro-o-toluidine	95-69-2	未检出 ND	---	---	---	30
2-萘胺 2-naphtylamine	91-59-8	未检出 ND	---	---	---	30
邻氨基偶氮甲苯 o-aminoazotoluene	97-56-3	未检出 ND	---	---	---	30
5-硝基-邻甲苯胺 5-nitro-o-toluidine	99-55-8	未检出 ND	---	---	---	30
对氯苯胺 p-chloroaniline	106-47-8	未检出 ND	---	---	---	30
二氨基苯甲醚 2,4-diaminoanisoale	615-05-4	未检出 ND	---	---	---	30
4, 4-二氨基二苯甲烷 4,4'-diaminodiphenyl methane	101-77-9	未检出 ND	---	---	---	30
3, 3-二氯联苯胺 3,3'-dichlorobenzidine	91-94-1	未检出 ND	---	---	---	30
3, 3-二甲氧基联苯胺 3,3'-dimethoxybenzidine	119-90-4	未检出 ND	---	---	---	30
3, 3-二甲基联苯胺 3,3'- dimethylbenzidine	119-93-7	未检出 ND	---	---	---	30
3, 3-二甲基-4, 4-二氨基二苯甲烷 3,3'-dimethyl-4,4'-diaminodiphenyl methane	838-88-0	未检出 ND	---	---	---	30
2-甲氧基-5-甲基苯胺 p- cresidine	120-71-8	未检出 ND	---	---	---	30

样品编号 Specimen No.		1+2	---	---	---	限值 Limit (mg/kg)
测试项目 Test Item	CAS No.	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	结果 Result (mg/kg)	
4, 4-次甲基双（2-氯苯胺） 4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	未检出 ND	---	---	---	30
4, 4-二氨基二苯醚 4,4'-oxydianiline	101-80-4	未检出 ND	---	---	---	30
4, 4-二氨基二苯硫醚 4,4'-thiodianiline	139-65-1	未检出 ND	---	---	---	30
邻甲苯胺 o-toluidine	95-53-4	未检出 ND	---	---	---	30
2, 4-二氨基甲苯 2,4-toluylenediamine	95-80-7	未检出 ND	---	---	---	30
2, 4, 5-三甲基苯胺 2,4,5-trimethylaniline	137-17-7	未检出 ND	---	---	---	30
邻茴香胺 o-anisidine	90-04-0	未检出 ND	---	---	---	30
2,4-二甲基苯胺 2,4 - xyldine	95-68-1	未检出 ND	---	---	---	30
2,6-二甲基苯胺 2,6 - xyldine	87-62-7	未检出 ND	---	---	---	30
结论 Conclusion		PASS 合格	---	---	---	

备注：
Note:
mg/kg =毫克每千克
mg/kg = milligrams per kilogram
LT =少于
LT = Less than; MT = More than
ND = 未检出 (报告检出限 = 5 mg/kg)
ND = Not detected (Reporting limit = 5 mg/kg)
混测结果基于样品的总质量来进行计算。
Composite results are based on total mass of the composite test portion.

详细结果

Detailed results

QB/T 1619-2018-票夹-配件质量^Φ

QB/T 1619-2018-Wallet-Accessories Quality^Φ

测试方法：QB/T 1619-2018 条款 6.4

Test method: QB/T 1619-2018 Clause 6.4

测试 Test	测试原理/要求 Test Principle / Requirement	结论 Conclusion
配件质量 Accessories Quality	经 200 次开关试验后，各附件能正常开关，无异常。 After 200 times of opening and closing test, the accessories can be switched on and off normally without abnormal.	符合 PASS

QB/T 1619-2018 票夹-条款 5.1.5 五金配件^Φ

QB/T 1619-2018 -Wallet -Clause 5.1.5 Hardware Fitting Properties^Φ

测试方法：电镀层 QB/T 2002.1-2018

Test method: Electroplating layer QB/T 2002.1-2018

测试条款 Test Clause	测试项目 Test Item	结论 Conclusion
4.1	外观质量 Appearance Quality	符合 PASS
4.2	电镀层结合强度 Bonding Strength of Electroplating layer	符合 PASS
4.3	漆膜附着力 Paint Adhesion	符合 PASS
4.4	耐腐蚀性 Resistance to Corrosion	符合 PASS

详细结果

Detailed results

QB/T 1619-2018-票夹-外观质量和缝制要求

QB/T 1619-2018-Wallet-Appearance Quality

测试方法：QB/T 1619-2018, 5.2, 目测

Test Method: QB/T 1619-2018, 5.2, Visual Check

样品编号		29	
Specimen No.			
测试项目	要求	不符合项	结论
Test Item(s)	Standard Requirement	Failed Item(s)	Conclusion
整体外观	形体饱满，弧线自然，粘贴平服，角对称，整洁干净	无	符合
Overall appearance	The appearance is plump; the arc line is natural, paste is flat, angles are symmetrical; basically upright clean and tidy	None	Meet
面 层 材料 Shell fabric	皮革、再生革	无	符合
	Leather and reproduced leather	None	
	厚薄均匀，无裂面、裂浆、脱色现象。表面平服，前面无伤残，背面可有粗糙斑两处，面积不大于 9 mm ² 。可有不明显印道、折痕 2 处		
	Uniform in thickness, without cracked grain, crazing or discoloration phenomenon. The surface is flat; the front and rear surfaces are without breakage; two rough spots are allowed to exist at the back surface and the bottom with area not larger than9mm ² . Two unobvious creases are allowed to exist		
	人造革/合成革	N/A	
	Artificial leather, synthetic leather		
	织物	无	符合
	Fabric	None	
	主要部位无断经、断纬，无跳丝、跳线、明显印道、污点、瑕点，次要部位可有轻微缺陷 2 处		
	The main position is without broken warp, broken weft, skipped silk, skipped thread, visible impression, stain and defect; two minor defects are allowed to exist at the minor position		
	毛皮	N/A	符合
	Fur		
	毛被基本平顺、灵活松散、洁净，无钩针，无明显掉毛、油毛、结毛。染色牢固，无浮色，无明显色花、色差（特殊效应除外）等缺陷		
	The coat is basically smooth, flexible, loose, clean, no crochet, no obvious hair loss, grease hair, hair formation; Dyeing firm, no float color, no obvious color tone, color difference (except special effect) and other defects.		
	其他材料	无	符合
	Other Materials	None	
	无影响使用的缺陷		
	No defects affecting use		
里心、隔仓	装配平服整齐，可有不明显的轻微伤残、粗糙斑	无	符合
Inner center and compartment	Flat, regular, clean, and tidy; There are allowed to minor injuries and rough spots that are not obvious.	None	Meet
包边	平直整齐，宽窄一致。方角不翘角、露角。圆角圆正，裱花均匀	N/A	N/A
Binding	Straight and neat, with consistent width. The square corners are not warped or exposed. Rounded corners, even pleats		
粘合质量	粘合牢固，不脱胶	无	符合
Bonding quality	Firmly bonded without delamination	None	Meet

样品编号 Specimen No.		29	
缝合线 Threads	选用适合所用面料、里料质量的缝线，质量与各部位相适应 Adopt suture suitable for the quality of shell fabric and lining fabric; the quality, color and luster shall be appropriate to each position	无 None	符合 Meet
线迹 Stitching line	上下线吻合，线迹顺直、均匀，针距基本一致。前面不允许空针、漏针、跳针、浮线、双针眼，不应有超过 15mm 长的线迹歪斜；单个产品上空针、漏针、跳针各不应超过 1 处，空针、漏针、跳针各不应超过 2 针；折边部位无漏缝 The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches, skipping stitches, floating line and double needle eye are not allowed on the bag surface. Stitching line skewness is not allowed. The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches and skipping stitches are not allowed on the front main bag surface and front lid; Stitching line skewness of over 15mm is not allowed; more than 2 empty stitches, missing stitches or skipping stitches are not allowed on more than 1 position of the products. No leaks in the folded edges.	无 None	符合 Meet
针距 Needle pitch	6 针/30 mm~14 针/30 mm 6 needles/30mm~14 needles/30mm	无 None	符合 Meet
缝线边距 Stitch margin	1.5mm~3.0mm（装饰线除外） 1.5mm~3.0mm (Except decorative lines)	无 None	符合 Meet
拉链 Zipper	缝合平直，边距一致；拉合滑顺，无错位、掉牙，不掉色 The suture is straight and even, the side distances are consistent, the opening and closing of zipper is smooth; without misalignment, off teeth and discoloration.	无 None	符合 Meet
配件 Auxiliaries	光滑、无毛刺。五金配件光亮无锈残，镀层均匀、无漏镀，不应有明显针孔、起皮、脱落，背面可有轻微划痕 Bright; without rust, damage, missing plating and burr, There should be no obvious pinholes, peeling or peeling, and there may be slight scratches on the back.	无 None	符合 Meet
配件安装 Installation of auxiliaries	平服、牢固、端正 Flat, firm and upright	无 None	符合 Meet
结论 Conclusion		合格 PASS	

样品编号 Specimen No.		30		
测试项目 Test Item(s)		要求 Standard Requirement	不符合项 Failed Item(s)	结论 Conclusion
整体外观 Overall appearance		形体饱满，弧线自然，粘贴平服，角对称，整洁干净 The appearance is plump; the arc line is natural, paste is flat, angles are symmetrical; basically upright clean and tidy	无 None	符合 Meet
面 层 材料 Shell fabric	皮革、再生革 Leather and reproduced leather	厚薄均匀，无裂面、裂浆、脱色现象。表面平服，前面无伤残，背面可有粗糙斑两处，面积不大于 9 mm ² 。可有不明显印道、折痕 2 处	无 None	符合 Meet





样品编号 Specimen No.			30	
		Uniform in thickness, without cracked grain, crazing or discoloration phenomenon. The surface is flat; the front and rear surfaces are without breakage; two rough spots are allowed to exist at the back surface and the bottom with area not larger than 9mm ² . Two unobvious creases are allowed to exist		
	人造革/合成革 Artificial leather, synthetic leather	无明显印道、凹凸、疙瘩 Without visible impression, unevenness and pimple	N/A	
	织物 Fabric	主要部位无断经、断纬，无跳丝、跳线、明显印道、污点、瑕点，次要部位可有轻微缺陷 2 处 The main position is without broken warp, broken weft, skipped silk, skipped thread, visible impression, stain and defect; two minor defects are allowed to exist at the minor position	无 None	
	毛皮 Fur	毛被基本平顺、灵活松散、洁净，无钩针，无明显掉毛、油毛、结毛。染色牢固，无浮色，无明显色花、色差（特殊效应除外）等缺陷 The coat is basically smooth, flexible, loose, clean, no crochet, no obvious hair loss, grease hair, hair formation; Dyeing firm, no float color, no obvious color tone, color difference (except special effect) and other defects.	N/A	
	其他材料 Other Materials	无影响使用的缺陷 No defects affecting use	无 None	
	里心、隔仓 Inner center and compartment	装配平整整齐，可有不明明显的轻微伤残、粗糙斑 Flat, regular, clean, and tidy; There are allowed to minor injuries and rough spots that are not obvious.	无 None	符合 Meet
	包边 Binding	平直整齐，宽窄一致。方角不翘角、露角。圆角圆正，裱花均匀 Straight and neat, with consistent width. The square corners are not warped or exposed. Rounded corners, even pleats	N/A	N/A
	粘合质量 Bonding quality	粘合牢固，不脱胶 Firmly bonded without delamination	无 None	符合 Meet
	缝合线 Threads	选用适合所用面料、里料质量的缝线，质量与各部位相适应 Adopt suture suitable for the quality of shell fabric and lining fabric; the quality, color and luster shall be appropriate to each position	无 None	符合 Meet
	线迹 Stitching line	上下线吻合，线迹顺直、均匀，针距基本一致。前面不允许空针、漏针、跳针、浮线、双针眼，不应有超过 15mm 长的线迹歪斜；单个产品上空针、漏针、跳针各不应超过 1 处，空针、漏针、跳针各不应超过 2 针；折边部位无漏缝 The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches, skipping stitches, floating line and double needle eye are not allowed on the bag surface. Stitching line skewness is not allowed. The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches and skipping stitches are not allowed on the front main bag surface and front lid; Stitching line skewness of over 15mm is not allowed; more than 2 empty stitches, missing stitches or skipping stitches are not allowed on more than 1 position of the products. No leaks in the folded edges.	无 None	符合 Meet





样品编号 Specimen No.		30	
针距 Needle pitch	6 针/30 mm~14 针/30 mm 6 needles/30mm~14 needles/30mm	无 None	符合 Meet
缝线边距 Stitch margin	1.5mm~3.0mm (装饰线除外) 1.5mm~3.0mm (Except decorative lines)	无 None	符合 Meet
拉链 Zipper	缝合平直, 边距一致; 拉合滑顺, 无错位、掉牙, 不掉色 The suture is straight and even, the side distances are consistent, the opening and closing of zipper is smooth; without misalignment, off teeth and discoloration.	无 None	符合 Meet
配件 Auxiliaries	光滑、无毛刺。五金配件光亮无锈残, 镀层均匀、无漏镀, 不应有 明显针孔、起皮、脱落, 背面可有轻微划痕 Bright; without rust, damage, missing plating and burr, There should be no obvious pinholes, peeling or peeling, and there may be slight scratches on the back.	无 None	符合 Meet
配件安装 Installation of auxiliaries	平服、牢固、端正 Flat, firm and upright	无 None	符合 Meet
结论 Conclusion		合格 PASS	

样品编号 Specimen No.		31	
测试项目 Test Item(s)	要求 Standard Requirement	不符合项 Failed Item(s)	结论 Conclusion
整体外观 Overall appearance	形体饱满, 弧线自然, 粘贴平服, 角对称, 整洁干净 The appearance is plump; the arc line is natural, paste is flat, angles are symmetrical; basically upright clean and tidy	无 None	符合 Meet
面 层 材料 Shell fabric	皮革、再生革 Leather and reproduced leather	无 None	符合 Meet
	人造革/合成革 Artificial leather, synthetic leather	N/A	
	织物 Fabric	无 None	
	毛皮 Fur	N/A	





样品编号 Specimen No.			31	
		float color, no obvious color tone, color difference (except special effect) and other defects.		
	其他材料 Other Materials	无影响使用的缺陷 No defects affecting use	无 None	
里心、隔仓 Inner center and compartment	装配平服整齐, 可有不明显的轻微伤残、粗糙斑 Flat, regular, clean, and tidy; There are allowed to minor injuries and rough spots that are not obvious.		无 None	符合 Meet
包边 Binding	平直整齐, 宽窄一致。方角不翘角、露角。圆角圆正, 桐花均匀 Straight and neat, with consistent width. The square corners are not warped or exposed. Rounded corners, even pleats		N/A	N/A
粘合质量 Bonding quality	粘合牢固, 不脱胶 Firmly bonded without delamination		无 None	符合 Meet
缝合线 Threads	选用适合所用面料、里料质量的缝线, 质量与各部位相适应 Adopt suture suitable for the quality of shell fabric and lining fabric; the quality, color and luster shall be appropriate to each position		无 None	符合 Meet
线迹 Stitching line	上下线吻合, 线迹顺直、均匀, 针距基本一致。前面不允许空针、漏针、跳针、浮线、双针眼, 不应有超过 15mm 长的线迹歪斜; 单个产品上空针、漏针、跳针各不应超过 1 处, 空针、漏针、跳针各不应超过 2 针; 折边部位无漏缝 The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches, skipping stitches, floating line and double needle eye are not allowed on the bag surface. Stitching line skewness is not allowed. The upper and lower threads are matched and the stitching line is straight; empty stitches, missing stitches and skipping stitches are not allowed on the front main bag surface and front lid; Stitching line skewness of over 15mm is not allowed; more than 2 empty stitches, missing stitches or skipping stitches are not allowed on more than 1 position of the products. No leaks in the folded edges.		无 None	符合 Meet
针距 Needle pitch	6 针/30 mm~14 针/30 mm 6 needles/30mm~14 needles/30mm		无 None	符合 Meet
缝线边距 Stitch margin	1.5mm~3.0mm (装饰线除外) 1.5mm~3.0mm (Except decorative lines)		无 None	符合 Meet
拉链 Zipper	缝合平直, 边距一致; 拉合滑顺, 无错位、掉牙, 不掉色 The suture is straight and even, the side distances are consistent, the opening and closing of zipper is smooth; without misalignment, off teeth and discoloration.		无 None	符合 Meet
配件 Auxiliaries	光滑、无毛刺。五金配件光亮无锈残, 镀层均匀、无漏镀, 不应有明显针孔、起皮、脱落, 背面可有轻微划痕 Bright; without rust, damage, missing plating and burr, There should be no obvious pinholes, peeling or peeling, and there may be slight scratches on the back.		无 None	符合 Meet
配件安装 Installation of auxiliaries	平服、牢固、端正 Flat, firm and upright		无 None	符合 Meet
结论 Conclusion			合格 PASS	

Remark: N/A = not applicable 不适用



详细结果

Detailed results

QB/T 1619-2018-票夹-拉链耐用度（200 次）

QB/T 1619-2018-Wallet-Zipper Durability (200 cycles)

测试方法：QB/T 1619-2018, 条款 6.5

Test Method: QB/T 1619-2018 Clause 6.5

样品编号 Specimen No.	29	要求 Requirement
测试项目 Test Item	结果 Inspection	
200 次后 After 200 Cycles	无破损 No damage	无破损 No damage

样品编号 Specimen No.	30	要求 Requirement
测试项目 Test Item	结果 Inspection	
200 次后 After 200 Cycles	无破损 No damage	无破损 No damage

样品编号 Specimen No.	31	要求 Requirement
测试项目 Test Item	结果 Inspection	
200 次后 After 200 Cycles	无破损 No damage	无破损 No damage



详细结果
Detailed results

QB/T 1619-2018-票夹-皮革摩擦色牢度
QB/T 1619-2018-Wallet-Colour Fastness to Rubbing In Leather

测试方法：QB/T 1619-2018, 附录 B
Test Method: QB/T 1619-2018, Appendix B

样品编号 Specimen No.	1	8	---	---	---	要求 Client's requirement
测试项目 Items	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	
干擦（100 转） Dry staining (100 Revolutions)	4-5	4-5	---	---	---	≥3
湿擦（20 转） Wet staining (20 Revolutions)	4-5	4-5	---	---	---	≥2-3
结论 Conclusion	合格 PASS	合格 PASS	---	---	---	

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.





详细结果
Detailed results

QB/T 1619-2018-票夹-纺织材料摩擦色牢度
QB/T 1619-2018-Wallet-Colour Fastness to Rubbing In Textiles

测试方法：GB/T 29865-2013
Test Method: GB/T 29865-2013

样品编号 Specimen No.	4	---	---	---	---	要求 Client's requirement
测试项目 Items	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	结果 Result (Grade)	
干擦 Dry	4-5	---	---	---	---	≥3-4
湿擦 Wet	4-5	---	---	---	---	≥2-3
结论 Conclusion	合格 PASS	---	---	---	---	

Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.



Verify Report



样本描述
Specimen description

样本编号 Specimen #	样本描述 Specimen description	部位 Location
1	Grey leather 灰色皮	Shell(all styles) 面料
2	Nude/grey leather 肤色/灰色皮	Shell(318 240 0200) 钥匙扣带子
3	Grey fabric 灰色布	Zipper tape(315 240 0200/315 240 0300/315 240 0400) 拉链布
4	Grey fabric 灰色布	Pocket lining(315 240 0200/315 240 0300/315 240 0400) 包口袋内里 0400)
5	Grey fabric 灰色布	Lining zipper tape(315 240 0200) 内里 拉链布
6	White mesh fabric 白色网布	Pocket lining/lining backing(315 240 0200/315 240 0300/315 240 0400) 口袋内里/内里被衬
8	Black synthetic leather 黑色合成革	Pocket lining/lining bottom(315 240 0200) 中间口袋内里/内里底部
29	Grey wallet with wrist strap 带腕带的灰色钱包	Entire article(315 240 0200) 整体
30	Grey phone pouch 灰色手机袋	Entire article(315 240 0300) 整体
31	Grey small wallet 灰色小钱包	Entire article(315 240 0400) 整体



Verify Report



图片 Pictures

样品图片：
Sample photo:



报告结束
End of the report

本报告中的测试结果和结论仅与收到的样品和本报告所述测试的方法/法规部分有关。如果报告中没有进一步说明，符合性声明基于启迈判定规则，详见 (<https://www.qima.com/conditions-of-service#decisionRule>)。未经启迈（杭州）检测有限公司书面批准，本检测报告不允许全部或者部分复制。

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and the method /regulation section(s) tested as described herein. If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule. (<https://www.qima.com/conditions-of-service#decisionRule>). This test report may not be reproduced in whole or in part, without the written approval of QIMA (Hangzhou) Testing Co., Ltd.



Verify Report